



Technical Data Sheet

Quality Specification

Palm Flute High Performance 1

	Basis Weight	SCT, CD	SCT, CD	CMT 30	CMT 30
Dimension	[g/m ²]	[kN/m]	[kN/m]	[N]	[N]
Standard	ISO 536	ISO 9895	ISO 9895	ISO 7263	ISO 7263
Tolerance	± 3 %	Average per Delivery	Minimum per Reel	Average per Delivery	Minimum per Reel
	125	2,80	2,60	270	250
	130	2,85	2,65	280	260
	140	3,30	3,10	320	300
	150	3,50	3,30	340	320
	160	3,75	3,55	360	340
	170	3,95	3,75	380	360
	180	4,15	3,95		
	190	4,30	4,10		
	200	4,45	4,25		
	210	4,60	4,40		
	220	5,04	4,80		

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 7,5 - 9 %

Sizing: Cobb₆₀ < 30 g/m² on request

Issue date 1 October 2025