



Technical Data Sheet

Quality Specification

Palm Flute High Performance 2

	Basis Weight	SCT, CD	SCT, CD	CMT 30	CMT 30
Dimension	[g/m ²]	[kN/m]	[kN/m]	[N]	[N]
Standard	ISO 536	ISO 9895	ISO 9895	ISO 7263	ISO 7263
Tolerance	± 3 %	Average per Delivery	Minimum per Reel	Average per Delivery	Minimum per Reel
	135	2.75	2.60	270	250
	140	2.90	2.70	300	280
	150	3.20	3.00	330	300
	160	3.30	3.15	340	320
	165	3.50	3.30	350	330
	170	3.60	3.35	360	340
	175	3.65	3.40	370	350
	180	3.70	3.50	380	360

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb₆₀ < 35 g/m² on request
Cobb₁₈₀₀ < 155 g/m² on request

Issue date 01.01.2016