



Technical Data Sheet

Quality Specification

Palm High Performance Liner

	Basis Weight	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 %	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	90	205	2.28	1.86	1.71
	100	228	2.28	2.05	1.90
	110	251	2.28	2.24	2.09
	130	286	2.20	2.49	2.34
	150	330	2.20	2.85	2.70
	160	352	2.20	3.03	2.88
	170	374	2.20	3.21	3.06

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 7,5 - 9 %

Sizing: Cobb₆₀ < 35 g/m² on request

Issue date 1 October 2025