



Technical Data Sheet

Quality Specification

Palm Kraft Descartes

	Basis Weight	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 % ≤ 200 g/m ² ± 4 % > 200 g/m ²	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	135	351	2,60	2,90	2,60
	140	380	2,70	3,00	2,70
	150	390	2,60	3,10	2,80
	160	410	2,60	3,30	3,00
	170	440	2,60	3,50	3,20
	200	460	2,30	3,95	3,65

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb₁₈₀₀ < 155 g/m²

Issue date 1 January 2023