



Technical Data Sheet

Quality Specification

Palm Kraft

	Basis Weight	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 % ≤ 200 g/m ² ± 4 % > 200 g/m ²	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	140	380	2.7	2.9	2.6
	160	410	2.6	3.3	3.0
	170	440	2.6	3.5	3.2
	190	460	2.4	3.8	3.5
	210	480	2.3	4.1	3.8
	200	500	2.2	4.2	3,95

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb₁₈₀₀ < 155 g/m²

Issue Date 01.07.2018