



Technical Data Sheet

Quality Specification

Palm Topliner

	Basis Weigth	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 %	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	135	297	2.2	2.50	2.45
	150	330	2.2	2.85	2.70
	160	352	2.2	3.00	2.90
	180	430	2.4	3.15	3.05

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb₆₀ < 35 g/m² on request

Issue Date 01.01.2016