



Technical Data Sheet

Quality Specification

Palm Twin

	Basis Weight	Bursting Strength	Burst Index	SCT, CD	SCT, CD	CMT 30	CMT 30
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]	[N]	[N]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895	ISO 7263	ISO 7263
Tolerance	± 3 %	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel	Average per Delivery	Minimum per Reel
	90	180	2.0	1.60	1.50	-	-
	95	190	2.0	1.65	1.55	-	-
	100	200	2.0	1.70	1.60	-	-
	105	210	2.0	1.80	1.70	170	160
	110	220	2.0	1.90	1.80	180	170
	115	230	2.0	2.00	1.90	185	175
	130	260	2.0	2.25	2.10	210	200
	150	300	2.0	2.55	2.40	230	220

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Issue date 01.01.2019