



Technical Data Sheet

Quality Specification

Testliner 2

| | Basis Weight | Bursting Strength | Burst Index | SCT, CD | SCT, CD |
|-----------|--|---------------------|-------------------------|-------------------------|---------------------|
| Dimension | [g/m ²] | [kPa] | [kPa m ² /g] | [kN/m] | [kN/m] |
| Standard | ISO 536 | ISO 2759 | ISO 2759 | ISO 9895 | ISO 9895 |
| Tolerance | ± 3 % ≤ 200 g/m ² ± 4 % > 200 g/m ² | Minimum per Reel | Minimum per Reel | Average per Delivery | Minimum per Reel |
| | 100 | 250 | 2.5 | 1.76 | 1.60 |
| | 105 | 263 | 2.5 | 1.84 | 1.68 |
| | 110 | 275 | 2.5 | 1.93 | 1.76 |
| | 115 | 288 | 2.5 | 2.01 | 1.84 |
| | 120 | 300 | 2.5 | 2.09 | 1.92 |
| | 125 | 313 | 2.5 | 2.18 | 2.00 |
| | 130 | 325 | 2.5 | 2.29 | 2.10 |
| | 140 | 350 | 2.5 | 2.40 | 2.25 |
| | 150 | 375 | 2.5 | 2.55 | 2.40 |
| | 160 | 400 | 2.5 | 2.72 | 2.60 |
| | 170 | 425 | 2.5 | 2.90 | 2.75 |
| | 180 | 432 | 2.4 | 3.00 | 2.90 |
| | 190 | 456 | 2.4 | 3.20 | 3.10 |
| | 200 | 480 | 2.4 | 3.40 | 3.20 |
| | 210 | 485 | 2.3 | 3.50 | 3.35 |
| | 220 | 490 | 2.2 | 3.70 | 3.55 |

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb₆₀ < 35 g/m² on request

Issue date 01.01.2016