



Technical Data Sheet

Quality Specification

Waste Based Fluting

	Basis Weight	SCT, CD	SCT, CD	CMT 30	CMT 30
Dimension	[g/m ²]	[kN/m]	[kN/m]	[N]	[N]
Standard	ISO 536	ISO 9895	ISO 9895	ISO 7263	ISO 7263
Tolerance	± 3 %	Average per Delivery	Minimum per Reel	Average per Delivery	Minimum per Reel
	70	1.20	1.10	-	-
	80	1.40	1.30	-	-
	85	1.50	1.40	-	-
	90	1.60	1.50	-	-
	95	1.65	1.55	-	-
	100	1.70	1.60	-	-
	105	1.80	1.70	170	160
	110	1.90	1.80	180	170
	115	1.95	1.85	185	175
	120	2.00	1.90	190	180
	125	2.10	2.00	200	190
	130	2.20	2.10	210	200
	135	2.25	2.15	215	205
	140	2.30	2.20	220	210
	150	2.40	2.30	230	220
	160	2.50	2.40	240	230
	170	2.60	2.50	250	240
	180	2.70	2.60	260	250

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Issue date 01.01.2019