



Fiche technique

Caractéristiques techniques

Cannelure

	Grammage	SCT, _{ST}	SCT, _{ST}	CMT 30	CMT 30
Unité	[g/m ²]	[kN/m]	[kN/m]	[N]	[N]
Norme	ISO 536	ISO 9895	ISO 9895	ISO 7263	ISO 7263
Tolérance	± 3 %	moyenne par lot	mini par bobine	moyenne par lot	mini par bobine
70		1,20	1,10	-	-
75		1,30	1,20		
80		1,40	1,30	-	-
85		1,50	1,40	-	-
90		1,60	1,50	-	-
95		1,65	1,55	-	-
100		1,70	1,60	-	-
105		1,80	1,70	170	160
110		1,90	1,80	180	170
115		1,95	1,85	185	175
120		2,00	1,90	190	180
125		2,10	2,00	200	190
130		2,20	2,10	210	200
135		2,25	2,15	215	205
140		2,30	2,20	220	210
150		2,40	2,30	230	220
160		2,50	2,40	240	230
170		2,60	2,50	250	240

Conditions d'analyse : ISO 187, 23°C, 50 % H. R.

Humidité : 6,5 - 9 %

Mis à jour le 01.01.2022