



Technical Data Sheet

Quality Specification

Palm Cover

	Basis Weight	Bulk	Brightness	Cobb ₆₀	Opacity	Roughness (TS/BS) Bendsen
Dimension	[g/m ²]	[cm ³ /g]	[%]	[g/m ²]	[%]	[ml/min]
Standard	ISO 536	ISO 534	ISO 2470	ISO 535	ISO 2471	ISO 8791-2
	40.0	1.3 - 1.5	58	20.0	93.0	100 - 200
	45.0	1.3 - 1.5	58	20.0	94.0	100 - 200

Colour Specification:	Standard ISO 5631 L* (C/2°) 83.1 a* (C/2°) -0.5 - 0.0 b* (C/2°) 3.5 - 4.5
Preconditioning:	ISO 187, 23°C, 50% relative humidity
Tolerance:	The tolerances are within the industrial standard range
Certificates:	ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC (Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.)
PrePress Guidelines:	ICC Paper Profile: PSO_SNP_Paper_eci.icc Characterisation data: FOGRA42L.txt
Characteristic	Durable, clean and spill resistant, ideally suited for Flexographic printing and can be laminated
Raw Material:	100 % recycled fibre

Issue date 1st January 2024