



Technical Data Sheet

Palm News

	Basis Weight	Bulk	Brightness	Breaking Length (MD)	Opacity	Roughness (TS/BS) Bendtsen
Dimension	[g/m ²]	[cm ³ /g]	[%]	[m]	[%]	[ml/min]
Standard	ISO 536	ISO 534	ISO 2470	ISO 1924	ISO 2471	ISO 8791-2
	40.0	1.3 - 1.5	57	5,500	93.0	100 - 200
	42.5	1.3 - 1.5	57	5,500	93.5	100 - 200
	45.0	1.3 - 1.5	57	5,500	94.0	100 - 200
	48.8	1.3 - 1.5	57	5,500	95.0	100 - 200
	52.0	1.3 - 1.5	57	5,500	96.0	100 - 200

Colour Specification:	Standard ISO 5631	L* (C/2°) 82.0 a* (C/2°) -0.5 - 0.0 b* (C/2°) 3.5 - 4.5
Preconditioning:	ISO 187, 23°C, 50% relative humidity	
Tolerance:	The tolerances are within the industrial standard range, subject to production variations.	
Certificates:	ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC, Blue Angel, EU Ecolabel (Eltmann) (Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.)	
PrePress Guidelines:	ICC Paper Profile: PSO_SNP_Paper_eci.icc Characterisation data: FOGRA42L.txt	
Raw Material:	100 % recycled	

Issue date 16 February 2026

www.palm.de