



Technical Data Sheet

Quality Specification

Palm Top 60 H

	Basis Weight	Bulk	Brightness	Breaking Length (MD)	Opacity	Roughness (TS/BS) Bendtsen
Dimension	[g/m ²]	[cm ³ /g]	[%]	[m]	[%]	[ml/min]
Standard	ISO 536	ISO 534	ISO 2470	ISO 1924	ISO 2471	ISO 8791-2
	40.0	1.2	60	5,500	92.0	40
	42.5	1.2	60	5,500	93.0	40
	45.0	1.2	60	5,500	94.0	40
	48.8	1.2	60	5,500	95.0	40

Colour Specification: **Standard**
 ISO 5631 L* (C/2°) 83.1
 a* (C/2°) 0.0
 b* (C/2°) 3.5

Preconditioning: ISO 187, 23°C, 50% relative humidity

Tolerance: The tolerances are within the industrial standard range.

Certificates: ISO 9001, ISO 14001, OHSAS 18001, ISO 50001, FSC®, PEFC, Blue Angel
 The Eltmann mill produces paper which is EU Ecolabel compliant.

PrePress Guidelines: ICC Paper Profile: PSO_INP_Paper_eci.icc
 Characterisation data: FOGRA48L.txt

Issue date 01.07.2018