



## Technical Data Sheet

### Palm Top 68 H

|           | Basis Weight        | Bulk                 | Brightness | Breaking Length (MD) | Opacity  | Roughness (TS/BS) Bendtsen | Gloss Hunter (75°) |
|-----------|---------------------|----------------------|------------|----------------------|----------|----------------------------|--------------------|
| Dimension | [g/m <sup>2</sup> ] | [cm <sup>3</sup> /g] | [%]        | [m]                  | [%]      | [ml/min]                   | [%]                |
| Standard  | ISO 536             | ISO 534              | ISO 2470   | ISO 1924             | ISO 2471 | ISO 8791-2                 | ISO 8254-1         |
|           | 45.0                | 1.2                  | 68         | 5,500                | 94.0     | 40                         | 22                 |
|           | 48.8                | 1.2                  | 68         | 5,500                | 95.0     | 40                         | 22                 |
|           | 52.0                | 1.2                  | 68         | 5,500                | 96.0     | 40                         | 22                 |

|                              |                                                                                                                                               |                |
|------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------|----------------|
| <b>Colour Specification:</b> | <b>Standard</b>                                                                                                                               |                |
|                              | ISO 5631                                                                                                                                      | L* (C/2°) 85.0 |
|                              |                                                                                                                                               | a* (C/2°) 0.0  |
|                              |                                                                                                                                               | b* (C/2°) 3.5  |
| <b>Preconditioning:</b>      | ISO 187, 23°C, 50% relative humidity                                                                                                          |                |
| <b>Tolerance:</b>            | The tolerances are within the industrial standard range, subject to production variations.                                                    |                |
| <b>Certificates:</b>         | ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC, Blue Angel<br>(Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.) |                |
| <b>PrePress Guidelines:</b>  | ICC Paper Profile: PSO_INP_Paper_eci.icc<br>Characterisation data: FOGRA48L.txt                                                               |                |
| <b>Raw Material:</b>         | 100 % recycled                                                                                                                                |                |

Issue date 15 March 2023

[www.palm.de](http://www.palm.de)